

Lustran ABS H950

ISO Shortname: ISO 2580-1 -ABS 0, MG, 115-04-16-25

Property	Test Condition	Unit	Standard	Value
Rheological properties				
Molding shrinkage, normal	60x60x2	%	ISO 294-4	0.5 - 0.7
Melt volume-flow rate	220 °C; 10 kg	cm ³ /(10 min)	ISO 1133	4
Molding shrinkage, parallel	60x60x2	%	ISO 294-4	0.5 - 0.7
Mechanical properties (23 °C/50 % r. h.)				
Yield stress	50 mm/min	MPa	ISO 527-1,-2	50
Tensile Strain at break	50 mm/min	%	acc. ISO 527-1,-2	> 15
Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	2600
Flexural strength	2 mm/min	MPa	ISO 178	80
Flexural modulus	2 mm/min	MPa	ISO 178	2600
Izod notched impact strength	23 °C	kJ/m ²	ISO 180-1A	17
Izod notched impact strength	-30 °C	kJ/m ²	ISO 180-1A	8
Yield strain	50 mm/min	%	ISO 527-1,-2	2.9
Charpy impact strength	23 °C	kJ/m ²	ISO 179-1eU	140
Charpy impact strength	-30 °C	kJ/m ²	ISO 179-1eU	90
Charpy notched impact strength	23 °C	kJ/m ²	ISO 179-1eA	16
Charpy notched impact strength	-30 °C	kJ/m ²	ISO 179-1eA	7
Ball indentation hardness		N/mm ²	ISO 2039-1	110
Thermal properties				
Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	101
Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	108
Vicat softening temperature	50 N; 50 °C/h	°C	ISO 306	113
Burning behavior UL 94 (1.6 mm)	1.6 mm	Class	UL 94	HB
Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.7
Burning rate (US-FMVSS)	2.0 mm	mm/min	ISO 3795	55
Glow wire test (GWFI)	2.0 mm	°C	IEC 60695-2-12	700
Electrical properties (23 °C/50 % r. h.)				
Relative permittivity	100 Hz	-	IEC 60250	3.2
Relative permittivity	1 MHz	-	IEC 60250	3.0
Dissipation factor	100 Hz	10 ⁻⁴	IEC 60250	60
Dissipation factor	1 MHz	10 ⁻⁴	IEC 60250	100
Volume resistivity		Ohm·m	IEC 60093	1E14
Surface resistivity		Ohm	IEC 60093	1E16
Electric strength	1 mm	kV/mm	IEC 60243-1	37
Other properties (23 °C)				
Density		g/cm ³	ISO 1183	1.050
Processing conditions for test specimens				
Injection molding-Melt temperature		°C	ISO 294	240

Lustran ABS H950

Property	Test Condition	Unit	Standard	Value
Injection molding-Mold temperature		°C	ISO 294	70
Injection molding-Injection velocity		mm/s	ISO 294	240

Disclaimer

Styrolution (Thailand) Co., Ltd. 4/2 I-8 road, Map Ta Phut Industrial Estate, Rayong, Thailand