

Triax 1220S

High melt stability, excellent low-temperature toughness, good thermoformability.

ISO Shortname: [ABS+PA]

Property	Test Condition	Unit	Standard	Value	
				d.a.m.	cond.
Rheological properties					
C Melt volume-flow rate	260 °C; 5 kg	cm ³ /(10 min)	ISO 1133	2.8	
Molding shrinkage, parallel	150x105x3; 260 °C / MT 80 °C; 300 bar	%	acc. ISO 2577	1,1	1,05
Molding shrinkage, normal	150x105x3; 260 °C / MT 80 °C; 300 bar	%	acc. ISO 2577	1.25	1.1
Post- shrinkage, parallel	150x105x3; 80 °C; 1 h	%	acc. ISO 2577	0.03	
Post- shrinkage, normal	150x105x3; 80 °C; 1 h	%	acc. ISO 2577	0.03	
C Molding shrinkage, parallel	60x60x2; 260 °C / MT 80 °C; 500 bar	%	ISO 294-4	0,7	
C Molding shrinkage, normal	60x60x2; 260 °C / MT 80 °C; 500 bar	%	ISO 294-4	0,8	
Post- shrinkage, parallel	60x60x2; 80 °C; 1 h	%	ISO 294-4	0,1	
Post- shrinkage, normal	60x60x2; 80 °C; 1 h	%	ISO 294-4	0,1	
Mechanical properties (23 °C/50 % r. h.)					
C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	1700	950
C Yield stress	50 mm/min	MPa	ISO 527-1,-2	39	29
C Yield strain	50 mm/min	%	ISO 527-1,-2	3.5	13
C Nominal strain at break	50 mm/min	%	ISO 527-1,-2	>= 50	>= 100
C Charpy impact strength	23 °C	kJ/m ²	ISO 179-1eU	N	N
C Charpy impact strength	-30 °C	kJ/m ²	ISO 179-1eU	N	N
C Charpy notched impact strength	23 °C	kJ/m ²	ISO 179-1eA	72	>= 72
C Charpy notched impact strength	-30 °C	kJ/m ²	ISO 179-1eA	23	>= 25
Izod impact strength	23 °C	kJ/m ²	ISO 180-1U	N	N
Izod impact strength	-30 °C	kJ/m ²	ISO 180-1U	N	N
Izod notched impact strength	23 °C	kJ/m ²	ISO 180-1A	70	>= 70
Izod notched impact strength	-30 °C	kJ/m ²	ISO 180-1A	23	>= 25
Flexural modulus	2 mm/min	MPa	ISO 178	1600	950
Flexural strength	2 mm/min	MPa	ISO 178	56	36
Flexural strain at flexural strength	2 mm/min	%	ISO 178	5.6	6.9
Flexural stress at 3.5 % strain	2 mm/min	MPa	ISO 178	50	28
Thermal properties					
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	64	89
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	91	96
C Vicat softening temperature	50 N; 50 °C/h	°C	ISO 306	97	92
Vicat softening temperature	10 N; 120 °C/h	°C	ISO 306	185	165
C Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	1.05	
C Coefficient of linear thermal expansion, transverse	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	1.15	

Triax 1220S

Property	Test Condition	Unit	Standard	Value	
				d.a.m.	cond.
C Burning behavior UL 94 (1.6 mm)	1.5 mm	Class	UL 94	HB	
Other properties (23 °C)					
C Water absorption (Saturation value)	Water at 23 °C	%	ISO 62	~6	
C Water absorption (Equilibrium value)	23 °C; 50 % RH	%	ISO 62	~1,7	
C Density		kg/m ³	ISO 1183	1060	
Processing conditions for test specimens					
C Injection molding-Melt temperature		°C	ISO 294	260	
C Injection molding-Mold temperature		°C	ISO 294	80	
C Injection molding-Injection velocity		mm/s	ISO 294	40	

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Disclaimer

Disclaimer for sales products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold and our advisory service is given in accordance with the current version of our General Conditions of Sale and Delivery.

Test values

Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the colouring.

Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

Conditioning

Conditioning in accordance with ISO 1110 (70°C; 62% r.H.)

INEOS ABS (Deutschland) GmbH, D-50769 Köln

© INEOS ABS (Deutschland)